

# Bridge Paint

## spraying recommendations

**Spray trials by Graco and Wagner resulted in the following recommendations for spraying Murobond Bridge Paint;**

– HVLP recommended.

**The following options have been successfully tested;**

- Graco, Inc. HVLP using a number 4 fluid set and thinning with up to 5% clean water.
- Titan or Wagner HVLP using a number 4 fluid set and thinning with up to 5% clean water.
- Wagner Zip 52 double diaphragm pump using DeVilbiss ADV with 1.8mm – 2.2mm fluid set

Airless and air-assisted testing showed the higher pressure tended to make the product pack out lines and/or tips and should only be considered by contractors with experience in spraying mica-ceous iron oxide products.

Issue date: June 2017

**MUROBOND**