

WATER SHEETING CONDITIONER

An aqueous emulsion that increases the early setting and water resistance of Murobond Cement Paint.

Murobond's WSC is a water based additive formulated to increase the early cure of Murobond Cement Paint for. This reduces water penetration and increases weather resistance over the life of the Murobond cement coating.

FEATURES

- *For use on parapet walls or other highly exposed areas*
- *Added to the mixing water before mixing Murobond*
- *Single pack, water clean-up*
- *Murobond mixed with the addition of WSC is applied as normal*

USES

WSC is advised for Murobond applied to walls in exposed conditions such as parapet walls and

is particularly advised when strong colours are being used.

SPECIFICATIONS

WSC is only for use as an additive to Murobond Cement paint.

Packaging
Available in 1,4,10,15 litre

Issue date: July 2023

MUROBOND

SUMMARY OF TYPICAL APPLICATIONS & PROPERTIES

<i>Product Type</i>	Additive to increase setting of cement	
<i>Appearance</i>	Brownish aqueous solution	
<i>Colour Range</i>	N/A	
<i>Components</i>	1	
<i>Volume Solids</i>	34% by weight	
<i>VOC</i>	45 grams per litre	
<i>Flash Point</i>	N/A	
<i>Specific Gravity</i>	1.02	
<i>Solids</i>	31% by weight	
<i>Thinning</i>	According to label directions	
<i>Application Conditions</i>	Minimum	Maximum
<i>Air Temperature</i>	10°C	32°C
<i>Surface Temperature</i>	10°C	32°C
<i>Humidity</i>	85%RH	
<i>Wet Film Thickness Per Coat</i>	N/A	
<i>Dry Film Thickness Per Coat</i>	N/A	
<i>Suitable Surfaces</i>	Bare masonry - as Murobond Cement Paint	
<i>Application Method</i>	N/A	
<i>Typical Spreading Rate</i>	N/A	

TEMPERATURE	HUMIDITY	TOUCH DRY	RECOAT (MIN)	RECOAT (MAX)
15°C	50%	2-3 Hours	12 Hours	Unlimited
20°C	50%	1-2 Hours	12 Hours	Unlimited
25°C	50%	1-2 Hours	12 Hours	Unlimited
Full Cure	30 Days			

Issue date: July 2023

MUROBOND

TYPICAL SURFACE SYSTEMS

SURFACE	FIRST COAT	SECOND COAT	THIRD COAT
Exposed Masonry	Murobond with WSC	Murobond with WSC	
Exposed Cement Paint	Murobond with WSC	Murobond with WSC	
Exposed Lime paint	Murobond Sealer and Binder	Murobond with WSC	Murobond with WSC
Exposed Concrete	Murobond Sealer and Binder	Murobond with WSC	Murobond with WSC

SURFACE PREPARATION

As for Murobond Cement Paint

APPLICATION

Stir before use. Dilute to label directions before use. That is 1 part WSC to 4 parts clean water. This WSC solution is then used in place of mixing water when mixing Murobond Cement Paint.

Clean Up

Water

PRECAUTIONS

Ensure adequate ventilation during use.

Protect painted surface from rain for at least 4 hours after application.

Maintenance

As for Murobond Cement Paint.

Preparation to repaint

As for Murobond Cement Paint.

Storage

No special requirements. This product is not hazardous. Avoid storing in hot conditions (above 30°C) for extended periods

ENVIRONMENT

VOC for this product: 45 grams per litre APAS target level: No equivalent product. (Australian Paint Approval Scheme compliance level).

Issue date: July 2023

MUROBOND